

FABRIC SPECIFICATION

Page 1

QUALITY: **2394 RAVEN SLIT**

ISSUE DATE: 11/2/20 ISSUE N° 4

USEABLE WIDTH: 190 cm. min. (BS EN 1773:1997)

FINISHED YIELD: 109 g/m² ± 5 % (BS EN 12127:1998)

FINISHED ENDS: 55.5 per cm. ± 2 % (BS EN 1049-2:1994)

FINISHED PICKS: 53 per cm. ± 5 % (BS EN 1049-2:1994)

FIBRE CONTENT: 100% Polyester (PET)

PHYSICAL PROPERTIES

	<u>LENGTH</u>	<u>WIDTH</u>	
TENSILE STRENGTH:	> 650 N	> 625 N	(BS EN ISO 13934-1:2013)
ELMENDORF TEAR:	> 5.5 N	> 5.0 N	(BS EN ISO 13937-1:2000)
STRETCH ~	0 - 6 %	0 - 6 %	(TM-25 75mm strip,44N loading)
.. Residual extension:	0.1 %	0.0 %	(1 min. @ 44N)
STABILITY ~			
.. Wash Stability:	0.0 - 1.5 %	0.5 - 2.0 %	(BS EN ISO 6330:2012 5M @ 50°C)
.. WIRA Steam:	0.0 - 1.5 %	0.5 - 2.0 %	(BS 4323:1979)
.. Thermal:	0.0 - 1.5 %	0.5 - 2.0 %	(Hotplate: 3 min. @ 180°C)

For more information please contact our Technical Department.

COLOUR MATCHING

Visual matching:	Commercial match to standard under Artificial Daylight tubes.
Instrumental matching:	Maximum ΔE 1.0 using the CMC(2:1) equation (BS EN ISO 105-J03:1997) D ₆₅ illuminant, 10° observer data, Spectraflash 600+ spectrophotometer.
Within batch levelness:	Maximum ΔE 0.5.

Form: 'B-DEV-11' Ver.: 6, 27/8/14